

DURABILITY

4.0 Select Clear High Solids Clearcoat

A 2K High Solids Clearcoat designed to offer maximum productivity and glamour appearance. Depth and shine are achieved with just two coats. Designed for ease-of-polishing and allows quick polishing even after aggressive sanding of film. System remains easy-to-polish even after two weeks. Film hardens to the standards of even the toughest fleet finishes. U-TECH 4.0 Select Clear offers excellent durability and high gloss and can be applied over Polybase or Polybase Plus, in as little as 20 minutes at 70 °F.



Product Features

- Excellent gloss
- Fast air dry times
- Exceptional value
- Easy application
- Easy polishing

Technical Data:

Mixing Ratio:	4:1	Flash Time:	5 Minutes
Substrates:	Existing Finishes	Dust Free:	60 Minutes @ 70 °F
	Polybase or Polybase Plus	Tack Free: A40 Fast	1 Hour @ 70 °F
	All Cured U-TECH Single Stage Systems	A40 Medium	1.2 Hours @ 70 °F
		A40 Slow	1.5 Hours @ 70 °F
Film Build:	1.2 - 1.5 Mil per Single Coat	Dry to Polish Bake:	30 minutes @ 140 °F
Coats:	2		with 995
Potlife @ 70 °F	2 Hours @ 70 °F 3 Hours with 3 oz./gal. 995 3.5 Hours with 3 oz./gal. 996 1.0 Hours with 994 Super Accelerator	Ready-to-Spray VOC:	4.1 lb./gal.
		Air dry-to-Polish Times:	Overnight 6 Hours with 995 Block Accelerator 5 Hours with 996 Super Accelerator 4 Hours with 994 Super Accelerator
Gun Setup:	HVLP Gravity (1.4 - 1.5)	HVLP Siphon (1.8 - 2.2)	Pressure Feed (1.0 - 1.2)



U-TECH

DRIVEN BY DURABILITY



9000-8006